



TEST REPORT

1. NO : CT19-026234

2. Client

○ Name : roVa Corporation

○ Address : 18F 382, Gangnam-daero, Gangnam-gu, Seoul, Korea 06232

Reissuance(R1)

Date : 2019.04.24

3. Date of Test : 2019.02.25 ~ 2019.04.24

4. Use of Report : Quality control

5. Test Sample : roVa Shield Top coat

6. Test Method

(1) KS M ISO 2813:2015

(2) KS M 6020:2014

(3) KS M ISO 11890-2:2014

7. Test Results



1) roVa Shield Top coat

Test Item(s)	Unit	Test Method	Test Results	Remark
Gloss(60°)	-	(1)	5	(23 ± 2) °C, (50 ± 5) % R.H.
Recoatality	-	(2)	Passed	(23 ± 1) °C, (50 ± 4) % R.H.

2) Rova shield top coat

Test Item(s)	Unit	Test Method	Test Results	Remark
VOCs	g/L	(3)	1.67	-

----- End of Report -----

Affirmation	Tested By	Technical Manager
	Name : Seok Ho Song 	Name : Sang Bok Bae 

Our report apply only to the standards or procedures identified and to the sample(s) tested unless otherwise specified. The test results are not indicative of representative of the qualities of the lot from which the sample was taken or of apparently identical or similar products. The authenticity of this test report can be checked on KCL website(www.kcl.re.kr).

2019.04.24

Korea Conformity Laboratories President Yoon, Kap Seok 

Address : 08503 199, Gasan digital 1-ro, Geumcheon-gu, Seoul, Korea 82-2-2102-2500

Result Inquiry : Chemical Analysis Center 82-2-2102-2673

