4191-1275-1992-5961

TEST REPORT

COPY NOT

1. NO : CT22-010062E
2. Client
   - ○ Name : roVa Corporation
   - ○ Address : 18F 382, Gangnam-daero, Gangnam-gu, Seoul, Korea 06232
3. Date of Test : 2022.01.21 ~ 2022.03.17
4. Use of Report : Quality control
5. Test Sample : roVa Shield
6. Test Method
   (1) KS M ISO 2811-1:2016
   (2) KS M 5000:2019
   (3) KS M 6010:2014
   (4) KS M 6020:2014

Affirmation	Tested By Name : Lee, jeoung yun 이정윤	Technical Manager Name : Park Dong Hyup

1. Our report apply only to the standards or procedures identified and to the sample(s) tested unless otherwise specified.
2. The test results are not indicative of representative of the qualities of 3. the lot from which the sample was taken or of apparently identical or similar products.
3. The results of using only a portion of this report cannot be guaranteed.
4. The authenticity of this test report can be checked on KCL website(www.kcl.re.kr)

2022.03.17

Korea Conformity Laboratories President Jo, Yung Tae

TEST REPORT

COPY SAMPLE

No : CT22-010062E

7. Test Results

1) roVa Shield

Test Item(s)	Unit	Test Method	Test Results	Remark
Density	g/㎤	(1)	0.62	(23 ± 0.5) ℃
Consistency	K.U	(2)	87	(25 ± 0.5) ℃
Working properties	-	(2)	Passed	(23 ± 1) ℃, (50 ± 4) % R.H.
Condition in container	-	(2)	Passed	-
Drying time(Dry-Hard)	min	(3)	30	(23 ± 1) ℃, (50 ± 4) % R.H.
Appearance for dried films	-	(2)	Passed	(23 ± 1) ℃, (50 ± 4) % R.H.
Recoatability	-	(4)	Passed	(23 ± 2) ℃, (50 ± 5) % R.H.
Alkali resistance	-	(3)	Passed	-
Storage stability	-	(3)	Passed	(23 ± 1) ℃, 48 h (49 ± 2) ℃, 14 d
Odor	-	(3)	Passed	-
Water resistance	-	(3)	Passed	-
Fungal resistance test (After 4 weeks)	-	(3)	8	(32.5 ± 0.6) ℃ (96.5 ± 2.0) % R.H.

—— End of Report ——

KCL
COPY SAMPLE